

# PETRONAS GREASE CLAY MG

## High Temperature for Heavy Duty with Organophilic Bentonite Grease with Solid Lubricant and High Base Oil Viscosity

PETRONAS Grease CLAY MG is a high temperature Organophilic Bentonite grease with solid lubricant specially developed for heavy duty industrial equipment with slow speed plain bearings where the capability of conventional greases may be exceeded by either continuous high temperature or cyclic conditions from normal to extremely high temperatures.

Formulated with selected mineral base oils enhanced with Organophilic Bentonite clay thickened, advanced anti-oxidant, anti-rust, Molybdenum Disulphide, Graphite, and corrosion inhibitor additives. PETRONAS Grease CLAY MG provides excellent high temperature performance, high load shock load capabilities.

PETRONAS Grease CLAY MG meets or exceed key industrial specifications.

### Applications

PETRONAS Grease CLAY MG is recommended for use in:

- lubrication of high temperature applications where conventional soap thickened greases will not perform.
- recommended for the lubrication of plain and anti-friction bearings operating continuously in the 150°C to 170 °C range or under conditions where bearings are repeatedly cycled from ambient to high temperatures.
- sugar mill bearings, open gears, cement mill journal bearings, furnace door gears, oven and slow speed cams.

Note: PETRONAS Grease CLAY MG is recommended for operating temperature range of -10°C to +180°C.

# PETRONAS GREASE CLAY MG

## High Temperature for Heavy Duty with Organophilic Bentonite Grease with Solid Lubricant and High Base Oil Viscosity

### Features and Benefits

Features	Benefits
Excellent anti-wear protection	Protects equipment components from excessive wear at high temperatures and provides long equipment life
Excellent load carrying capacity	Contains special additives which enables the grease to withstand heavy loads without losing the lubricant film
Friction reduction capabilities	Has friction reducing solid additives for extra protection on sliding metal surfaces
High rust & corrosion protection	Protects bearing surfaces against rust and corrosion, even when the grease is contaminated with water
High resistance to water and steam wash-out	Equipment protection and good lubrication even in presence of water or steam
High thermal and oxidation stability	Has good oxidation resistance and can withstand high operating temperatures without hardening or forming bearing deposits
High oil bleed control	Has a high controlled oil bleed and does not separate under storage

# PETRONAS GREASE CLAY MG

## High Temperature for Heavy Duty with Organophilic Bentonite Grease with Solid Lubricant and High Base Oil Viscosity

### Typical Properties

Characteristic	Method	Specification	CLAY MG
Thickener Type	-	Clay	Clay
NLGI	ASTM D217	1	1
Color	Visual	Black	Black
Worked Penetration, mm/10	ASTM D217	310 – 340	325
Worked Penetration 100.000x, Penetration Change, mm/10, Max.	ASTM D217	+20	+15
Oil Separation, Mass %, Max.	ASTM D1742	6	4
Dropping Point, °C, Min.	ASTM D2265	Non-Melt	Non-Melt
Four Ball Wear, mm, Max.	ASTM D2266	0.50	0.50
Four Ball EP Weld Point, Min.	ASTM D2596	200	250
Roll Stability, % of Penetration Change, Max.	ASTM D1831	20	10
Water Washout, %, Max.	ASTM D1264	10	5
Water Spray off, %, Max.	ASTM D4049	30	20
Water Resistance @90°C, Max.	DIN 51807:1	1	0
Rust Protection, rating	ASTM D1743	Pass	Pass
Base Oil Viscosity @40°C, cSt	ASTM D445	1450 - 1550	1500
Molybdenum Disulfide, Mass %	-	2	2
Graphite, Mass %	-	6	6

All technical data is provided for reference only / SS is available upon request including quality control limits

### Performance Levels

- DIN 51502 OGF1K-10
- ISO 12924 XCHB1

# PETRONAS GREASE CLAY MG

## High Temperature for Heavy Duty with Organophilic Bentonite Grease with Solid Lubricant and High Base Oil Viscosity

### Health, Safety and Environment

This product is unlikely to present any significant health and safety hazards when used in the recommended application. Avoid contact with skin. Wash immediately with soap and water after skin contact. Do not discharge into drains, soil or water.

For further detail regarding storage, safe handling, and disposal of product, please refer to product SDS or contact us at: [www.pli-petronas.com](http://www.pli-petronas.com)

### Important Note

The word PETRONAS, the PETRONAS logo and such other related trademarks and/or marks used herein are trademarks or registered trademarks of PETRONAS Lubricants International Sdn. Bhd. ("PLISB"), or its subsidiaries or related Holding Corporation under license unless indicated otherwise. The PLI Documents and the information contained herein is believed to be accurate as of the date of printing. PLISB makes no express or implied representation or warranties as to its accuracy or completeness or information in or any transaction performed. The PLI Documents information provided is based on standard tests under laboratory conditions and is given only as a guide. Users are advised to ensure that they refer to the latest version of these PLI Documents. It is the responsibility of the users to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations imposed by the respective local authorities.

Safety Data Sheets are available for all our products and should be only be consulted for appropriate information regarding storage, safe handling and disposal of the product. No responsibility shall be taken by either PLISB or its subsidiaries and related holding corporation for any loss or injury or any direct, indirect, special, exemplary, consequential damages or any damages whatsoever, whether in action of contract, negligence or other tortious action, in connection or resulting from abnormal use of the materials and/or information, from any failure to adhere to recommendations, or from hazards inherent in the nature of the materials and/or information. All products, services and information supplied are under our standard conditions of sale. Please consult with any of our local representative in the event you require any further information.