

PETRONAS GREASE CaSX

Premium Performance Calcium Sulphonate Complex Grease

PETRONAS Grease CaSX is a Calcium Sulphonate complex grease specially developed for both industrial, marine and off-road applications.

Formulated with mineral base oils enhanced with Calcium Sulphonate complex soap, anti-wear, anti-oxidant, anti-rust and corrosion inhibitor additives. PETRONAS Grease CaSX provides excellent load carrying capacity making it suitable for heavily loaded applications. Excellent mechanical stability, corrosion protection and water resistance which are important in wet and corrosive environments.

PETRONAS Grease CaSX meets or exceeds key industrial specifications.

Applications

PETRONAS Grease CaSX is recommended for use in:

- industrial, marine and off-road applications
- most heavy duty bearing applications including large plain and anti-friction bearings and other mechanisms requiring a high temperature NLGI 2 grease such as slides, cams etc.
- application that requiring multi-purpose grease and excels in Marine applications

Note: PETRONAS Grease CaSX is recommended for operating temperature range of -30°C to +160°C.

PETRONAS GREASE CaSX

Premium Performance Calcium Sulphonate Complex Grease

Features and Benefits

Features	Benefits
Excellent load carrying capacity	Contains special EP additives which enables the grease to withstand heavy loads without losing the lubricant film
Excellent rust & corrosion protection	Protects bearing surfaces against rust and corrosion, even when the grease is contaminated with water
Excellent thermal and oxidation stability	Has excellent oxidation resistance and can withstand high operating temperatures without hardening or forming bearing deposits
High pumpability	High performance where low temperature performance is required
High resistance to water wash-out	Protects equipment as the grease is not easily removed in presence of water
High adhesive and cohesive properties	High grease tenacity which helps reduce leakage and extend re-lubrication intervals, reducing maintenance costs
Mechanical stability	A highly stable grease with little or no change to consistency when worked in the lubrication of bearings.

PETRONAS GREASE CaSX

Premium Performance Calcium Sulphonate Complex Grease

Typical Properties

Characteristic	Method	Specification	CaSX
Thickener Type	-	Calcium Sulphonate Complex	Calcium Sulphonate Complex
NLGI	ASTM D217	2	2
Color	Visual	Brown	Brown
Worked Penetration, mm/10	ASTM D217	265 - 295	280
Worked Penetration 100.000x, Penetration Change, mm/10, Max.	ASTM D217	+10	+8
Oil Separation, Mass %, Max.	ASTM D1742	5	2
Dropping Point, °C, Min.	ASTM D2265	300	300
Four Ball Wear, mm, Max.	ASTM D2266	0.40	0.40
Four Ball EP Weld Point, Min.	ASTM D2596	620	620
Roll Stability, % of Penetration Change, Max.	ASTM D1831	10	5
Wheel Bearing Leakage, grams, Max.	ASTM D4290	8	5
Water Washout, %, Max.	ASTM D1264	5	1
Rust Protection, rating	ASTM D1743	Pass	Pass
Emcor Test (Salt Water), Max.	ASTM D6138	1-1	0-0
Water Resistance @90°C, Max.	DIN 51807:1	1	1
Base Oil Viscosity @40°C, cSt	ASTM D445	210 - 230	220

All technical data is provided for reference only / SS is available upon request including quality control limits

Performance Levels

- DIN 51502 KP2N-30
- ISO 12924 XCDIB2

PETRONAS GREASE CaSX

Premium Performance Calcium Sulphonate Complex Grease

Health, Safety and Environment

This product is unlikely to present any significant health and safety hazards when used in the recommended application. Avoid contact with skin. Wash immediately with soap and water after skin contact. Do not discharge into drains, soil or water.

For further detail regarding storage, safe handling, and disposal of product, please refer to product SDS or contact us at: www.pli-petronas.com

Important Note

The word PETRONAS, the PETRONAS logo and such other related trademarks and/or marks used herein are trademarks or registered trademarks of PETRONAS Lubricants International Sdn. Bhd. ("PLISB"), or its subsidiaries or related Holding Corporation under license unless indicated otherwise. The PLI Documents and the information contained herein is believed to be accurate as of the date of printing. PLISB makes no express or implied representation or warranties as to its accuracy or completeness or information in or any transaction performed. The PLI Documents information provided is based on standard tests under laboratory conditions and is given only as a guide. Users are advised to ensure that they refer to the latest version of these PLI Documents. It is the responsibility of the users to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations imposed by the respective local authorities.

Safety Data Sheets are available for all our products and should be only be consulted for appropriate information regarding storage, safe handling and disposal of the product. No responsibility shall be taken by either PLISB or its subsidiaries and related holding corporation for any loss or injury or any direct, indirect, special, exemplary, consequential damages or any damages whatsoever, whether in action of contract, negligence or other tortious action, in connection or resulting from abnormal use of the materials and/or information, from any failure to adhere to recommendations, or from hazards inherent in the nature of the materials and/or information. All products, services and information supplied are under our standard conditions of sale. Please consult with any of our local representative in the event you require any further information.